

Technical Data Sheet

Rubber Basecoat Waterproofer

Packaging Information:

- 1 Gallon Pail
- 5 Gallon Pail
- 55 Gallon Drum
- 250 Gallon Tote

Characteristics:

Rubber Basecoat is ideal for above and below- grade waterproofing applications including insulated concrete forms, foundations, basements, and more. Basecoat has 1200% elongation to resists cracking and peeling and can be used on concrete, masonry, wood, metal and more. Basecoat can also be used as a primer in many roof coating systems and has been Air Barrier Association of America evaluated.

VOLUME SOLIDS	46%
WEIGHT PER GALLON	ASTM D1475 8.36 lbs.
ADHESION TO VARIOUS SUBSTRATES	CMU – ASTM D4541 Method B 80.2 psi exceeds minimum Hardie Board – ASTM D4541 Method B 198.8 psi exceeds minimum DensGlass – ASTM D4541 Method B 43.3 exceeds minimum
COLOR	Translucent Blue
COVERAGE	1 gallon per 25 sq. ft. for waterproofing applications (2 coat min. for sprayer, 4 coat min. for roller) 1 gallon per 100 sq. ft. when used as a primer in roofing & deck applications
DRY FILM THICKNESS (@ 1 GAL/ 25 SQ. FEET)	7.5 Mils per coat (30 Mils total DFT for waterproofing)
DRY TIME	5 Mils DFT – Recoat in 2 hours 10 Mils DFT – Recoat in 3.5 hours
CURE TIME	7-10 days
ELONGATION	ASTM D2370 up to 1200%
FLASH POINT	>200°F
HUMIDITY	Best applied below 50% humidity
AIR PERMEANCE	ASTM E2178 Air Permeance 0.00010 cfm/ft² at 1.56lb/ft²
SEAM STRENGTH	ANSI 118.10 Section 4.2 114 lb./in-Perpendicular to Seam 46.3 lb./in-Parallel to Seam
MOLD & MILDEW RESISTANCE	ANSI 118.10 Section 4.1 No Growth
PH AS SHIPPED	ASTM E70 9.0 -9.5
BREAKING STRENGTH	ANSI 118.10 Section 4.3 1.540 psi Machine direction 512 psi Cross Direction
SHELF LIFE	24 Months Unopened
DIMENSIONAL STABILITY	ANSI 118.10 Section 4.4 -0.17% (70°C)
V.O.C CONTENT	< 1 g/l
VAPOR PERMEABILITY	ASTM E96 Desiccant Method 0.117 perms. Water Method 0.49 perms
VISCOSITY	ASTM D2196 4100 -5100 cps spindle #
SHEAR STRENGTH	ANSI 110.10 Section 5.0 138 psi (7 -day) 89.4 psi (7-day water immersion) 125 psi (Four-Week) 140 psi (twelve-Week) 76.6 psi (100 -day water immersion)

Compliance

SCAQMD	Yes
LEED®V4 & V4.1 EMMISIONS	Yes
LEED® V4 & V4.1 V.O.C	Yes
CARB & CARB SCM 2007	Yes
OTC & OTC PHASE II	Yes

Surface Prep:

All surfaces must be sound and free of frost, dirt, grease, oil, loose nails & screws, sharp protrusions, or other contaminants that will hinder the adhesion of the membrane installation. Clean loose dust and dirt from the surface by brushing or wiping with a clean, dry cloth brush or broom.

Concrete:

Should be cured in place for a minimum of 28 days. All concrete surfaces should have the appearance of 80 grit sandpaper to promote adhesion. All sharp protrusions such as cold joints shall be ground flush. Honeycomb, holes, cracks, and joints up to 5/8” across shall be filled with Trowel Grade Patch or Rubberized Caulk.

Concrete Masonry Unit:

Mortar joints shall be struck flush and free of voids exceeding 1/8” across. Mortar droppings shall be removed from brick ties and all other surfaces accepting Rubber Basecoat and accessories. Allow mortar joints to dry a minimum of 28 days prior to application of the Rubber Basecoat and accessories. The exposure duration or exposure conditions as required by the concrete manufacturer

OSB, Plywood, Lumber, Pressure-Treated Wood:

Wood and wood sheathing need to be flush at joints with gaps between boards according to building codes and manufacturers requirements. Moisture content, measured with a wood moisture meter in the core of the substrate, requirement is below 20%. Do not cover any wooden materials with Rubber Basecoat and/or accessories if moisture content is above 20%.

Application Methods:

Review product Application Guide before proceeding. Contact Kool Coats for questions pertaining to the coating system application and required coating film thickness. Conduct a test patch to ensure proper adhesion.

- Basecoat must be top coated with a high-quality acrylic paint for all exterior vertical wall exposures. On interior wall surfaces, Rubber Basecoat must be top coated with a high-quality acrylic paint for washability
- Basecoat used as a base coat on roofs must be top coated with an appropriate Ames topcoat
- Do not apply if the temperature is expected to drop below 32° F within 24hours of application or over wet substrates
- Do not apply in high heat areas of 180°F or more

Disclaimer:

The information and specifications set forth in this Technical Data Sheet are based on tests conducted by or on behalf of Kool Coats. All information is subject to change and pertains to the product available at time of publication. Please contact Kool Coats to receive the most recent Technical Data Sheet.

Clean Up, Storage & Disposal:

- Clean up application equipment, tools, spills, hands immediately after use with water
- Store unused product in the original container tightly sealed
- Dispose of this product in accordance with local, state, or federal requirements
- Protect from freezing

Cautions:

- Do not take internally
- Keep out of reach of children
- Avoid contact with skin and eyes
- Use hand and eye protection when using this product
- Wash with soap and water after contact with skin
- If eye-contact occurs rinse with clean water and seek medical advice if symptoms continue