



Basic Uses & Description:

RP-115 Silicone Pond Filler is a 100% silicone dispersion with various organic fillers to provide a tough, durable surface to fill low areas of a roof surface. This product is designed to be used in conjunction with the Kool Coats Silicone Roof Restoration system and can be applied over virtually any roof substrate. Although silicone coatings are resistant to ponding water, best roofing practices always call for eliminating ponding water to ensure the highest level of roof performance and to prevent premature failure of the system.

This product is a single component, moisture cure product that is ready-to-use for quick application and is UV stable. Suitable roof substrates include TPO, PVC, EPDM, modified bitumen, BUR (smooth & gravel surface), concrete, spray polyurethane foam and others. Pond Filler is also recommended for repairing small blisters in spray polyurethane foam roofs.

Application:

Prior to installation, the underlying deck should be examined to ensure the roof structure is sound and uncompromised. The ponding area should be marked to outline the deficient area. The depth of the ponding water should also be noted prior to application to ensure the proper application thickness of the Silicone Pond Filler. Powerwash the roof surface and then prime the surface per the chart below. Pour the product onto the ponding area and use a trowel to smooth and level it out to the desired thickness and profile. Prior to coating the field of the roof, install 15 to 30 mils of silicone coating over the Silicone Pond Filler to ensure the surface is properly sealed.

The typical coverage rate of a 3 gallon pail of Silicone Pond Filler is 10 square feet at a thickness of 1/2".

Storage & Handling:

Ponding Eliminator has a recommended shelf life of 12 months from date of manufacture when stored in unopened containers and between 40°F and 80°F.

Refer to product packaging.

Packaging Sizes:

RP-115 Silicone Pond Filler is available in 3 gallon containers.

TEST PROPERTY	TEST VALUE
Appearance	Gray Granular
Solids Content	99%
Weight per Gallon	15.8 lbs/gal
VOC Content	<14.46 g/L
Clean Up	Mineral Spirits
Tack-Free Time	60-90 min at 50% RH
Cure Time Through 1/4"	8 hrs @ 50% RH
Cure Time Through 1/2"	24 hrs @ 50% RH